## **PRODUCT SPECIFICATION**

## GLAZED FLOOR TILE 60 x 60cm / 24 x 24" & 12 x 24" Pressed Ceramic Tiles International Norms ISO 13006-10545/98 GROUP: B1b

| No. | lcon            | Test item                     | Unit | Requirements of Standard  |       | Test result  | Result                      |
|-----|-----------------|-------------------------------|------|---|-------|--------------|-----------------------------|
| 1   | <b>+++</b>      | Dimensional variation         | (%)  | length of side  | 0.6   | < 0.6        | Qualified                   |
| 2   | ↔               | Side straightness             | (%)  | ± 0.5   |       | < 0.5        | Qualified                   |
| 3   |                 | Squareness                    | (%)  | ± 0.5   |       | < 0.5        | Qualified                   |
| 4   | <u>↓     </u> ↓ | Surface flatness              | (%)  | Center curvature<br>degree  | ± 0.5 | < 0.5        | Qualified                   |
|     |                 |                               |      | Warping degree  | ± 0.5 | < 0.5        | Qualified                   |
|     |                 |                               |      | Side curvature<br>degree  | ± 0.5 | < 0.5        | Qualified                   |
| 5   | Q               | Surface quality               |      | Sighting vertically at a distance of<br>0.8 meter away from the tile<br>no defect on surface is observed in<br>at least 95% of the tile |       | conformed    | Qualified                   |
| 6   |                 | Water absorption              | (%)  | Average value ≤ 3<br>individual ≤ 3.3   |       | < 3<br>< 3   | Qualified                   |
| 7   |                 | Breaking strength             | N    | When thickness ≥ 7.5mm<br>the Average value ≥ 700   |       | >700         | Qualified                   |
| 8   |                 | Rupture modulus               | Мра  | Average value ≥ 30<br>individual ≥ 27   |       | > 30<br>> 30 | Qualified                   |
| 9   |                 | Abrasion resistance           | revs | > 1500  |       |              | Qualified<br>Class 3        |
| 10  | $\bigotimes$    | Scratch resistance            | мон  |   |       | > 6          | Qualified                   |
| 11  | 璨               | Frost resistance              |      | No cracking after test  |       | conformed    | Qualified                   |
| 12  | 4               | Resistance to acids & alkalis |      | not less than grade GB  |       | Grade GA     | Qualified                   |
| 13  |                 | Chemical resistance           |      | not less than grade GB  |       | Grade GA     | Qualified                   |
| 14  | Ľ               | Slip resistance               | R    | Ramp slip rating test   |       | R11          | Exterior Only<br>on request |
|     |                 |                               | DCoF | DCoF: 0.42  |       | >0.42        | Matt/Exterior               |